

Technical Information

Solutack 7410

Hotmelt Adhesive

Introduction

Solutack 7410 is an **ethylene-octene copolymer** produced via SOLUTACK™ technology. It performs well in general purpose of low melt viscosity polyolefin including polymer modification and hot melt adhesives.

Characteristics

- Low Density, Low Viscosity Polyolefin
- Good Flexibility
- Low Glass Transition Temperature
- Low Crystallinity

Properties

		Typical Values	Unit	Test Method
Physical Properties	Density	0.874	g/cm ³	ASTM D792
	Melt Index (2.16 kg @190°C)	1000	g/10min	SK Method ¹
Mechanical Properties	Tensile Strength at Break	1.85	MPa	ASTM D638
	Elongation at Break	120	%	ASTM D638
Thermal Properties	Melting Temperature	53, 78	°C	SK Method
	Glass Transition Temperature	-58	°C	SK Method
Viscosity	Brookfield Viscosity (177°C)	8.2	Pa·s	SK Method

¹ Estimated value ; Point is outside normal testing range. Calculated value *via* Advanced Rheological Expansion System (ARES)

Notes

These are **typical values** and are **not be construed as specifications**. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK Global Chemical Co.,LTD
26 Jong-ro, Jongno-gu,
Seoul, Korea
TEL +82-2-2121-6757

TS&D SK innovation Global Technology
325 Exporo, Yueseong-gu,
Daejeon, Korea
TEL +82-42-609-8952