

LLDPE FN810

YUCLAIR FN810 is octene-1 copolymer designed for use in stretch wrap film application. YUCLAIR FN810 provides stronger film than ones made from competitive LLDPE film grades. Therefore YUCLAIR FN810 shows superior tensile strength, tear strength, gel-free, cling property. Outstanding clarity and good processibility make this resin an ideal choice for film application when blended with conventional LDPE.

YUCLAIR FN810 can be processed readily into blown film using standard extrusion techniques. YUCLAIR FN810 complies with FDA regulations in 21 CFR177.1520 for all food contact.

Application / Use Case

Film / industrial film, STRETCH WRAP (CASTING)

Specification

	Specification	Unit	Test Method
Density	0.919	g/cm ³	ASTM D1505
Melt Index	0.9	g/10min	ASTM D1238
Additives	-		SK Method

Physical Properties

	Value	Unit	Test Method
Film Thickness	50	µm	ASTM D746
Softening Point(Vicat)	102	°C	ASTM D1525
Tensile Strength at Yield(MD)	120	kg/cm ²	ASTM D882
Tensile Strength at Yield(TD)	110	kg/cm ²	ASTM D882
Tensile Strength at Break(MD)	550	kg/cm ²	ASTM D882
Tensile Strength at Break(TD)	500	kg/cm ²	ASTM D882

Head Office 99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea

Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of 140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea

Technology Tel. 82-42-866-7624 Fax. 82-42-866-7603

Online www.skglobalchemical.com

www.skchem.com

ISO 9001 Certified





Elongation at Break(MD)	700	%	ASTM D882
Elongation at Break(TD)	800	%	ASTM D882
Tear Strength(MD)	18	g/μm	ASTM D1922
Tear Strength(TD)	23	g/μm	ASTM D1922
Spencer Impact Strength	13	kg·cm	ASTM D3420
Haze	17	%	ASTM D1003
Brittleness Temperature	<-80	°C	ASTM D746

These are typical properties only, and are not to be construed as specific limits.

Head Office

99 Seorin-dong, Jongno-gu, Seoul 110-110, Korea

Tel. 82-2-2121-5114 Fax. 82-2-2121-7001

SK Institute of
Technology

140-1 Woncheon-dong, Yuseong-gu, Taejeon, Korea

Tel. 82-42-866-7624 Fax. 82-42-866-7603

Online

www.skglobalchemical.com

www.skchem.com

ISO 9001 Certified

